

Technical data sheet

Hard and Soft Exotic Wood Undercoat



- blocks wood tannins and rust
- limits wood porosity
- suitable on acrylic and oil-based paint



PURPOSE

- V33 Hard and Soft Exotic Wood is suitable for all types of wood: tannic wood (oak, chestnut...), exotic wood (iroko, doussie...), porous wood (pinewood, larch), hardwood, old wood, autoclave wood and wood-based materials.
- It provides deep penetration of the wood and makes paint, stain or varnish adhere more easily.

CHARACTERISTICS

The neutral undercoat can be applied before interior or exterior varnish, or a wood stain.

The white undercoat can be used under paint to block the surface and tannins. It blocks porous wood and facilitates adhesion to exotic wood.

- It can be covered with oil-based or acrylic paint.
- It blocks tannins.
- It prevents stains from appearing on the finish paint.
- Extended durability of paints for wood, wood stains and varnish.

PREPARATION

The surface has to be clean, dry, not greasy, not flaking and resin-free. Round off the wood angles and edges by sanding. Fill in potential cracks and crevices, then sand and remove dust.

RAW WOOD: • **porous, old, deteriorated:** brush to remove all particles and loose fibres, then sand and remove dust.

- **exotic wood and softwood:** degrease and remove resin drippings with acetone, then sand and remove dust.
- **hard wood (chestnut, oak):** sand and remove dust. First treat the wood with V33 Exterior Wood Treatment, for better protection.
- **other types of wood :** sand and remove dust.

STAINED/PAINTED/VARNISHED WOOD:

- **thick film:** remove the film with V33 Wood Stripper, rinse, sand and remove dust.
- **thin film:** sand and remove dust.

APPLICATION

Ideal application conditions: between 12° and 25°. Mix the undercoat with a wide stick, stirring around the bottom of the can to mix it thoroughly. On a well-prepared surface, apply 1 or 2 coats depending on wood porosity. Apply each coat regularly, without excess paint and in a criss-cross pattern. Allow to dry for 4 hours and lightly sand between each coat or before applying the finish coat.

V33 TIPS

The hard and soft exotic wood undercoat has to be covered with a finish coat.

PRECAUTIONS FOR USE: SENSITIVE TO FROST. S2 : keep out of reach of children.

S29 : Do not throw residues in the sewer. S51 : Use only in well-ventilated areas.

EU limit value (A/g category): 30g/L (2010). This product contains 18g/L COV at the maximum.

Sizes: 0.5L-2.5L
Tool cleaning: water
Drying time: recoat: 4h
fully dry: 24h
Material: brush, roller
Coverage: +/- 12m²/L

